

ALU GLASS SCRIM LAMINATE

Technical data sheet

construction	
	18 µm alufoil
	glass scrim 2x2
	20 g/m ² coating FR

Technical data	unit	setpoint	tolerance	test
Total weight	g/m ²	84	+/- 20%	EN ISO 2286-2
Tensile strength (MD)	N/50 mm	250	+/- 20%	EN ISO 527-3
Tensile strength (CD)	N/50 mm	250	+/- 20%	EN ISO 527-3
Elongation (MD)	%	4	+/- 20%	EN ISO 527-3
Elongation (CD)	%	4	+/- 20%	EN ISO 527-3
Tear strength	N		+/- 20%	DIN 53357
Tear strength	N		+/- 20%	DIN 53357
Water vapour permeability	g/ m ² /d	< 0,03		EN 1921

Roll make-up

Standard widths	1000, 1050, 1500 mm
Core (cardboard)	76 mm

Our products are the result of fundamental research. They correspond to the latest technical standard. For their useful application we give data and technical information to the best of our knowledge but, however, without any warranty. In special cases the user shall make his own tests to determine the suitability of the products for his purpose.